



## 4 Results

### 4.1 Abrasion resistance (taber abraser) according ASTM D4060:1995

Sample:

Results:

Coating system Standard FEVE Coating Sample 1	Weight loss: 11.7 mg
Coating system Standard FEVE Coating Sample 2	Weight loss: 12.8 mg
Coating system Standard FEVE Coating Sample 3	Weight loss: 14.4 mg
Coating system «Coolest White» Sample 1	Weight loss: 6.4 mg
Coating system «Coolest White» Sample 2	Weight loss: 6.6 mg
Coating system «Coolest White» Sample 3	Weight loss: 7.5 mg
Coating system Standard PE Coating Sample 1	Weight loss: 16.1 mg
Coating system Standard PE Coating Sample 2	Weight loss: 15.6 mg
Coating system Standard PE Coating Sample 3	Weight loss: 16.0 mg